

ELR 10-72 WHT

Product Information

ELR 10-72 WHT is a High Performance, crossed linked polymer enhanced with proprietary Nano Technology. ELR 10-72 WHT is designed for custom roto casting where improved heat distortion is desired at elevated temperatures. ELR 10-72 WHT can be hand mixed or processed through plural component, high pressure or low pressure dispensing equipment. ELR 10-72 WHT exhibits excellent flow and wetting properties. Once fully cured, ELR 10-72 WHT is tough with excellent impact

Physical Properties (Components)

	Component A	Component B
Viscosity at 75°F (cps)	800 - 900	110 - 130
Specific Gravity (gr/ml)	1.13 – 1.15	0.97 – 0.99

Physical Properties (Final Product)

Hardness, Shore D, ASTM D-2240	70 - 75
Tensile Strength (psi), ASTM D-412	>4000
Elongation (%), ASTM D-412	>10
Color	White

Handling Characteristics

Mix Ratio by Volume (Component A: Component B)	50a / 50b
Mix Ratio by Weight	53a / 47b
Gel Time at 75°F (seconds)	120 - 180
Tack Free Time (seconds)	at Gel
Demold Time	10-20 minutes
90% Cure Time (hours)*	24

(*) Final physical properties will be reached in a course of several days.

Storage and Shelf Life

Components should be kept well sealed in a dry place from 70 to 90°F. Shelf life of unopened containers is six (6) months from manufacturing date. Mix Component B well prior to each use. Purge opened containers with dry nitrogen before resealing. Refer to product MSDS for more information.

Packaging

Component A:	55 gallon steel drum (closed top)	500 lb	Net Weight
Component B:	55 gallon steel drum (open top)	450 lb	Net Weight

Non-Warranty: This information is furnished without warranty, expressed or implied, except that is accurate to the best knowledge of Eteco, Inc. The data on these sheets relates only to the specific material designated herein. Eteco, Inc. assumes no legal responsibility for use or reliance upon this data. The user should conduct sufficient investigation to establish the suitability of any product for its intended use.

