

F 7203

Product Information

F 7203 is a high performance, flexible polyurethane foam designed for processing through plural component low or high pressure dispensing equipment. Once fully cured, this material is tough, flexible and dimensionally stable. F 7203 is designed for use in applications where tough skin is required with good memory and with excellent tensile strength.

Physical Properties (Components)

	Component A	Component B
Viscosity at 75°F (cps)	400 - 600	900 - 1300
Specific Gravity (gr/ml)	1.09 - 1.12	1.07 - 1.09

Physical Properties (Final Product)

Tensile Strength (psi), ASTM D-638	25
Elongation (%), ASTM D-638	90
Tear Strength (pli), ASTM D1004	10

Handling Characteristics

Mix Ratio by Weight (Component A/Component B)	50/50
Mix Ratio by Volume (Component A/Component B)	N/A
Cream Time (sec)	20 - 30
Rise Time (sec)	85 - 110
Tack Free Time (sec)	90 - 130
Demold Time (min)	10
Final Cure Time (hours)	1
Density (pcf)	3.0 – 3.6

Storage and Shelf Life

Components A and B should be kept well sealed in a dry place at a temperature from 75°-90°F. Shelf life of unopened containers is six (6) months from manufacturing date. Purge opened containers with dry nitrogen before resealing. Premix component B prior to use. Refer to product MSDS for more information.

Packaging

Component A:	55 gallon steel drum (closed top)	500 lbs	Net Weight
Component B:	55 gallon steel drum (open top)	450 lbs	Net Weight

Non-Warranty: This information is furnished without warranty, expressed or implied, except that is accurate to the best knowledge of Eteco, Inc. The data on these sheets relates only to the specific material designated herein. Eteco, Inc. assumes no legal responsibility for use or reliance upon this data. The user should conduct sufficient investigation to establish the suitability of any product for its intended use.