



Product Information

CG 603-18 A Blue is a versatile single component moisture cure 100% polyurethane adhesive that is sandable, paintable, and stainable. CG 603-18 A can be applied by roller, brush, towel, or dipped. CG 603-18 A Blue is temperature resistant and water resistant and exhibits excellent adhesion to primed metal, wood, polyurethane foam, ceramic, and concrete.

Physical Properties (Final Product)	Units	Test Method	Results
Color	-	Visual	Blue

Handling Characteristics	Units	Component A
Specific Gravity @ 75°F	g/mL	1.03 - 1.04
Viscosity @ 75°F	cPs	3200
Color	Visual	Pale Yellow
Gel Time @ 75°F	Minutes	16 - 20
Tack Free Time	Minutes	20 - 30
90% Cure Time*	Hours	24

Final properties will be reached in a course of several days. Properties are typical and not for specifications

Installation Recommendations

CG 603-18 A Blue is fully formulated and ready for use. Product temperature can be ambient during application onto substrates that are free of loose particles, oil, grease, dirt, etc. Apply one coat by brush, roller, or towel.

Application rate is 250-350 sqft. per gallon depending on substrate porosity and profile.

Prepare concrete surface using Abrasive Blast per SSPC 13.

Steel prep should be a minimum of SSPC 6.

Storage and Shelf Life

Components should be kept well sealed in a dry place from 70 to 90°F. Shelf life of unopened containers is six (6) months from manufacturing date. Mix Component B well prior to each use. Purge opened containers with dry nitrogen before resealing. Refer to product SDS for more information.

Packaging

Component A:	55 gallon steel drum (Closed Top)	490 lb Net Weight
Component A:	5 gallon plastic Pail (Open Top)	38 lb Net Weight

For more information contact Eteco, Inc. (714) 480-1370 | info@etecoinc.com
www.etecoinc.com

Non-Warranty: This information is furnished without warranty, expressed or implied, except that is accurate to the best knowledge of Eteco, Inc. The data on these sheets relates only to the specific material designated herein. Eteco, Inc. assumes no legal responsibility for use or reliance upon this data. The user should conduct sufficient investigation to establish the suitability of any product for its intended use.