



#### Product Information

SPL-H 4071 is a high-performance, multi-purpose 100% solid polyurethane coating designed to provide structural support to hot tubs and spas. SPL-H 4071 contains no styrene or HCFC's. SPL-H 4071 is an excellent replacement for Polyester resin and fiberglass. SPL-H 4071 is designed to be sprayed through most plural component high pressure dispensing equipment such as Gusmer, Graco and Glasscraft. SPL-H 4071 is tough, flexible with high impact and tear resistance.

Physical Properties (Final Product)	Units	Test Method	Results
Shore Hardness	Shore D	ASTM D-2240	70
Tensile Strength	psi	ASTM D-412	6,800
Flexural Modulus	psi	ASTM D-412	375,000
Elongation	%	ASTM D-412	5
Tear Strength	pli	ASTM D-624	180
Color	-	Visual	Natural/Pigmented

Handling Characteristics	Units	Component A	Component B
Mix Ratio by Volume	(A/B)	50	50
Mix Ratio by Weight	(A/B)	52	48
Specific Gravity @ 75°F	g/mL	1.16 - 1.18	1.06 - 1.08
Viscosity @ 75°F	cPs	400 - 600	900 - 1300
Color	Visual	Pale Yellow	Opaque/White
Gel Time @ 75°F	Seconds	25 - 35	
Tack Free Time	Seconds	15 - 20	
90% Cure Time*	Hours	24	

\*Final properties will be reached in a course of several days. Properties are typical and not for specifications\*

#### Storage and Shelf Life

Components should be kept well sealed in a dry place from 70 to 90°F. Shelf life of unopened containers is six (6) months from manufacturing date. Mix Component B well prior to each use. Purge opened containers with dry nitrogen before resealing. Refer to product SDS for more information.

#### Packaging

Component A:	55 gallon steel drum (closed top)	490 lb Net Weight
Component B:	55 gallon steel drum (open top)	435 lb Net Weight

**Non-Warranty:** This information is furnished without warranty, expressed or implied, except that is accurate to the best knowledge of Eteco, Inc. The data on these sheets relates only to the specific material designated herein. Eteco, Inc. assumes no legal responsibility for use or reliance upon this data. The user should conduct sufficient investigation to establish the suitability of any product for its intended use.